

Product Specification**965 Flooring and Tread Adhesive****1. PROPRIETARY PRODUCT****1.1. Proprietary Product:** 965 Flooring and Tread Adhesive**1.2. Manufacturer:**

Tarkett USA Inc.	Phone:	(800) 899-8916
30000 Aurora Rd.		
Solon, Ohio 44139	Tech:	Ext 9297
Web: www.tarkettna.com	Samples:	Ext 9299
E-mail: info@tarkett.com	Fax:	(440) 632-8920

1.2.1. Physical Characteristics:

- Base – Water Based Acrylic Adhesive
- Color – White Paste
- Shelf Life – 1 year at 65° F (18° C) to 85° F (30° C) and when stored in unopened, original container in a dry area.
- Freeze thaw up to 5 cycles at 20° F (-7° C)
- Drying Time – Approximately 15 minutes to 1 hour depending on temperature, relative humidity, and porosity of subfloor.
- Contains no hazardous or carcinogenic ingredients as defined by OSHA chemicals and meets all federal, state and local air quality regulations.
- SCAQMD Rule 1168 – VOC compliant (<10.0 g/l)

Rubber Tiles, Feature Strips, Vinyl Mouldings, Rubber and Vinyl Stair Treads, Vinyl Stair Nosings, Subfloor Leveler System, Tactile Warning Strips

Porous Floor:

Coverage 125-150 sq. ft. per Gallon
1/16 x 1/16 x 1/16 sq. notch trowel

Non-Porous Floor:

Coverage – 150-175 sq. ft. per Gallon
1/16 x 1/16 x 1/16 V notch trowel

Inertia, Triumph and Replay Sheet & Tile

Porous Floor:

Coverage 125-150 sq. ft. per Gallon
1/8 x 1/16 x 1/8 V notch trowel

Non-Porous Floor:

Coverage – 150-175 sq. ft. per Gallon
1/8 x 1/16 x 1/8 V notch trowel

2. INSTALLATION**2.1. General Installation Requirements:**

- Tarkett flooring and adhesives must be site conditioned at room temperature for a minimum of 48 hours prior to, during, and after installation. Room temperature must be maintained between 65° and 85°F (18° and 30°C) with HVAC system operating. A minimum temperature of 55°F (13°C) must be maintained afterwards. The ambient relative humidity should be between 40% and 60%.

- Floors shall be smooth, flat, permanently dry, clean and free of all foreign material such as dust, paint, grease, oils, and solvents, curing and hardening compounds, sealers, asphalt, and old adhesive residue.
- It is essential that moisture tests be taken on all concrete floors regardless of age and grade level. Perform three tests for the first 1000 sq. ft. then one test should be conducted for every 1,000 sq. ft. of flooring and the results not exceed 7 lbs. per 1,000 sq. ft. in 24 hours when tested in accordance with ASTM F 1869 Standard Test method for Measuring Vapor Emission Rate of Concrete Subfloor using Anhydrous Calcium Chloride. Or 85% when tested accordance with ASTM F 2170 Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs using in situ Probes. Surface pH of the concrete should range between 7 and 10. If the tests results exceed the limitations, the installation must not proceed until the problem has been corrected.

2.2. Manual: Refer to Adhesive container label for complete installation details.

3. AVAILABILITY AND COST

3.1. Available through authorized Tarkett distributors nationwide.

4. TRAFFIC:

- Restrict traffic for 24 hours after installation.
- No heavy traffic, rolling loads or furniture placement for 72 hours after installation.
- Wait 72 hours after installation before performing initial cleaning

5. LIMITED WARRANTY

Adhesive warranty is a "system warranty" covered under the product that is recommended to be installed in conjunction with this adhesive. Refer to Tarkett limited warranty for complete details.

6. TECHNICAL SERVICES

For current Installation and Maintenance Instructions, Product Specifications, Safety Data Sheet and other technical data, visit us on the web at www.tarkettna.com or contact Tarkett at (800) 899-8916.